



## Moulding Grade Physical Property Averages

Thickness	Target Density (lbs. per sq. ft)	Target IB (psi)	MOR (psi)	MOE (psi)	Face Screw Holding (lbs.)	Edge Screw Holding (lbs.)
3/8"	47.0	140	4200	410,000	-	-
1/2"	42.0	130	4000	410,000	225	-
9/16"	42.00	130	3300	340,000	225	-
5/8"	42.0	130	3300	340,000	225	200
11/16"	42.0	120	3300	340,000	225	200
3/4"	42.0	120	3300	340,000	225	200
1"	42.0	120	3300	340,000	225	200